

Seoul 5mm Loose lay specification		
Specification	Standard	LOOSE LAY
Total Thickness (mm)		5mm
Wear Layer (mm)		0.5mm
CE Certification		YES
Coating		UV coating
Embossing		BP surface
Bevelled		Micro Bevel
Click		NO CLICK
Fiberglass		Yes
Plank Size		1231x186mm (48.46"X7.32")
Plank per box		8
Sqm per Box		1.8317m ² (19.72 sqft)
Density		2000kg/m ³
Impact Sound Reduction	ASTM E2179-09	60 dB
Resistance to Chemicals	EN 423	Class 0
	ASTM F 925	PASS
Color Fastness	ISO 105-B02	≥6
Slip Resistance	DIN 51130	R10
Watertightness	EN13553	N/A
Wear Resistance	EN 660-2	Group T
Reaction to fire	EN13501-1	B fl -s1
	EN ISO 11925-2	Pass
	EN ISO 9239-1	pass
Water resistance		100%
Dimensional stability	ASTM F2199-09	× Direction: 0.05% Y Direction: -0.12%
Curling	ASTM F2199-09	-0.09mm
Residual indentation	ASTM F 1914-07	3%
Effect of acastor chair	EN425	No visible damage
Phthalates	CPSC-CH- C1001-09.3	PASS
Density of smoke	ASTM E 662-15a	PASS
Toxic Element Test	EN 71-3	PASS. Not toxic. Does not contain heavy metal and formaldehyde

